# **Drain** 11X™ Drainage Board

### **TECHNICAL DATA SHEET**





#### MATERIAL

DMX uses a specially formulated Polypropylene that provides a high environmental stress crack resistance to alkalines and acids found in the soil. In addition, DMX is made from 100% virgin resin.

Our special extrusion process utilizes low heat and low shear to prevent heat degradation in the final product.

The use of antioxidants and lubricants further ensure a smooth, superior quality membrane that outperforms the competition.

### PROPERTIES

The DMX Drain 11X<sup>™</sup> drainage board finished product has a 10mm dimple height, providing a drainage capacity of 18 gal/min/ft of width and a compressive strength of 11,000lbs/sq ft. Polypropylene is highly resistant to chemical interaction and has a life expectancy of up to 50 years when properly installed in accordance with the manufacturer's instruction

DRAINAGE CORE	TEST METHOD	IMPERIAL	METRIC
Colour	Black		
Dimensions (W x L)		4 x 50ft, 6 x 50ft	1.22 x 15.25m, 1.83 x 15.25m
Compressive Strength	ASTM D 1621	11000 psf (76 psi)	527 kNm <sup>2</sup>
Thickness	ASTM D 1777	7/16 inch	10 mm
Material	Polypropylene		
FILTER FABRIC	NON-WOVEN		
Grab Tensile Strength	ASTM D 4632	90 lbs	0.401 kN
Grab Elongation	ASTM D 4632	50%	50%
Trapezoid Tear Strength	ASTM D 4533	40 lbs	0.178 kN
CBR Puncture Resistance	ASTM D 6241	265 lbs	1.178 kN
Permittivity	ASTM D 4491	2.0 sec <sup>-1</sup>	2.0 sec <sup>-1</sup>
Water Flow	ASTM D 4491	150 gpm/ft <sup>2</sup>	6095 l/min/m <sup>2</sup>
Apparent Opening Size (AOS)	ASTM D 4751	50 Std. U.S. Sieve	0.300 mm
UV Resistance	ASTM D 4355	70%/500 hrs	70%/500 hrs
COMPOSITE SYSTEM			
Water Flow Rate (V)	ASTM D 4716	20 Gal/min/ft	248 L/min/m
Roll Size		4ft x 50ft, 6ft x 50ft	1.22m x 15.25m, 1.83m x 15.25m
Roll Weight		28 lbs	12.7 kg

## TECHNICAL DATA

DMX Membranes Limited. 165 Orenda Road, Brampton, Ontario L6W 1W3 Tel. (905) 458-8998 Fax: (905) 458-8994 www.dmxmembranes.com